

汽车修补漆树脂 Acrylic resin for automotive refinish

型 号 Product	外 观 Appearance	色 泽 Color (Fe-Co)	固体份 Non-volatile matter (%)	粘度(1)格式管, s; (2)标准粘度, mPa·s viscosity (1)Gardner (2)mPa·s(25℃)	酸价 Acidity (mgKOH/g)	羟基含量 OH content (100%)	溶 剂 Solvent	主要性能 Features	主要用途 Main application
K1-01	清澈透明 crystal clear	≤1	50±2	19(X)~50(Z2) 1300~3400	2~5		甲苯/醋酸丁酯 TOL/BAC	CAB相溶性好, 铝粉定位佳, 配套性好; Compatibility with CAB, aluminium orientation, adhesion to ABS plastic, inter-layer adhesion with top PU coat	1K树脂 1K resin
K1-02	清澈透明 crystal clear	≤1	50±2	19(X)~50(Z2) 1300~3400	2~5		甲苯/醋酸丁酯 TOL/BAC	CAB互溶, 铝粉定位性好, 双组份配套性好; Compatibility with CAB, aluminium orientation, adhesion to ABS plastic, inter-layer adhesion with top PU coat	1K树脂 1K resin
K1-03	清澈透明 crystal clear	≤1	50±2	19(X)~50(Z2) 1300~3400	2~5		二甲苯/PMA XYL/PMA	耐候性好, 颜料分散性好, CAB互溶, 铝粉定位性好, 双组份配套性好; Compatibility with CAB, pigment wetting and dispersion, aluminium orientation, adhesion to ABS plastic, inter-layer adhesion with top PU coat	1K树脂 1K resin
K2-01	清澈透明 crystal clear	≤1	60±2	34(Z)~91(Z4) 2300~6200	5~9	2.6%	二甲苯/PMA XYL/PMA	颜料润湿及分散性好, 耐候性佳、和CAB相溶性好; Pigment wetting, compatibility with CAB, durable, yellowing resistance	1K/2K 通用树脂 1K/2K universal resin
K2-02	清澈透明 crystal clear	≤1	60±2	9(U)~26(Y) 630~1800	5~9	2.7%	二甲苯/PMA XYL/PMA	颜料润湿及分散性; Pigment wetting, general performance	2K树脂 2K resin
K2-03	清澈透明 crystal clear	≤1	60±2	9(U)~26(Y) 630~1800	5~9	3.4%	二甲苯/PMA XYL/PMA	颜料润湿及分散性; Pigment wetting, general performance	2K树脂 2K resin
TA-01	清澈透明 crystal clear	≤1	70±2	16(W)~40(Z1) 1100~2700	5~9	3.2%	二甲苯/醋酸丁酯 XYL/BAC	丰满度、耐黄变性、耐候性、干性、流平性等性能优越; Hige solid, good film build, gross, durable, yellowing resistance, good drying, levelling, good appearance	清漆 Clearcoat
TA-02	清澈透明 crystal clear	≤1	70±2	26(Y)~68(Z3) 1800~4600	5~9	4.2%	二甲苯/PMA XYL/PMA	硬度高、鲜映性、光泽、耐候性、耐黄变性、流平性优越; High OH content, hardness, built, weathering resistance, yellowing resistance, good drying, levelling	清漆 Clearcoat
TC-01	清澈透明 crystal clear	≤1	70±2	50(Z2)~140(Z5) 3400~9900	7~11	2.5%	二甲苯/PMA XYL/PMA	通用树脂; 鲜映性、流平性、光泽好; Economy grade,gloss, levelling, durable	清漆 Clearcoat
TC-02	清澈透明 crystal clear	≤1	70±2	26(Y)~68(Z3) 1800~4600	7~11	3.0%	二甲苯/PMA XYL/PMA	通用树脂; 鲜映性、流平性、光泽好; Economy grade,gloss, levelling, durable	清漆 Clearcoat
TC-03	清澈透明 crystal clear	≤1	70±2	26(Y)~68(Z3) 1800~4600	7~10	3.2%	二甲苯/醋酸丁酯 XYL/BAC	通用树脂; 鲜映性、流平性、光泽好; Economy grade,gloss, levelling, durable	清漆 Clearcoat
TC-04	清澈透明 crystal clear	≤1	70±2	50(Z2)~140(Z5) 3400~9900	7~10	3.2%	二甲苯/醋酸丁酯 XYL/BAC	通用树脂; 鲜映性、流平性、光泽好; Economy grade,gloss, levelling, durable	清漆 Clearcoat
TK-01	清澈透明 crystal clear	≤1	70±2	68(Z3)~140(Z5) 4600~9900	5~9	3.0%	二甲苯/醋酸丁酯 XYL/BAC	快干、耐黄变性、耐候性、干性、流平性等性能优越; Fast drying, durable, yellowing resistance, levelling	清漆 Clearcoat
TK-02	清澈透明 crystal clear	≤1	70±2	68(Z3)~140(Z5) 4600~9900	6~11	4.0%	二甲苯/醋酸丁酯 XYL/BAC	快干、耐黄变性、耐候性、干性、流平性等性能优越; Fast drying, durable, yellowing resistance, levelling	清漆 Clearcoat