

聚丙烯PP塑料专用树脂 Thermoplastic resin for polypropylene plastic coat

型 号 Product	外 观 Appearance	固体份 Non-volatile matter (%)	粘度(1)格式管, s; (2)标准粘度, mPa · s viscosity (1)Gardner (2)mpa · s(25℃)	酸价 Acidity (mgKOH/g)	Tg (℃)	溶 剂 Solvent	主要性能 Features	主要用途 Main application
PP-04B	混浊、微黄 Slight yellow, not clear	40±2	5~20 400~1800	3~6	93	甲苯 TOL	PP件底漆, 各色面漆, 硬度比PP-03B高(汽车内饰件油漆); Adhesion to PP plastic, hardness, water resistance, compatibility with NC	PP塑料漆 PP coat
PP-08	混浊、微黄 Slight yellow, not clear	45±2	9(U)~26(Y) 630~1800	2~5	50	醋酸乙酯/醋酸丁酯 EAC/BAC	无苯环保型, PP底材上附着力好, 综合性能优; Benzene free, adhesion to PP plastic, hardness, water resistance	PP塑料漆 PP coat
PP-10A	混浊、微黄 Slight yellow, not clear	45±2	9(U)~26(Y) 630~1800	2~5	60	甲苯/MIBK TOL/MIBK	PP件底漆, 各色面漆, 金属漆, 耐水性能佳, 配套附着力好(耐沸水4小时、耐水240小时), 施工性能好; Adhesion to PP plastic, excellent water and boiling water resistance, compatibility with CAB, aluminium orientation	PP塑料漆 PP coat
PP-13A	混浊、微黄 Slight yellow, not clear	45±2	9(U)~26(Y) 630~1800	2~5	45	甲苯 TOL	PP件底漆, 各色面漆; Adhesion to PP plastic, water resistance	PP塑料漆 PP coat
PP-13B	混浊、微黄 Slight yellow, not clear	40±2	9(U)~26(Y) 630~1800	2~5	45	甲苯/MIBK TOL/MIBK	PP件底漆, 各色面漆, 金属漆; Adhesion to PP plastic, water resistance, compatibility with CAB, aluminium orientation	PP塑料漆 PP coat
PP-15	混浊、微黄 Slight yellow, not clear	40±2	5~20 400~1800	3~6	75	甲苯 TOL	PP件底漆, 各色面漆(耐沸水2小时); Adhesion to PP plastic, hardness, good water resistance	PP塑料漆 PP coat